



# BESTCHEM

## Technical Data Sheet

### NPP-0800 Clear Cracking Paste

#### Introduction

Cracking rubber paste for textile screen printing, transparent, excellent soft hand feeling, the cracking effect will become big if more times in printing, meets ISO6330, OEKO-TEX requirements.

#### Specification

- Ingredients: Acrylic Resin
- Appearance: Milky white clear
- Ion: Anion
- Solid Content:  $43 \pm 3\%$
- pH: 6-8
- Packing: 20, 30kg PE drum
- Storage: Store air-tight in ventilated area under 35°C, 12 months.

#### Using suggestion

- For light color fabric: print NPP-688C as background then print cracking paste (clear 100~90% + white 0~10%). It can move fabric after cracking in flat table
- For dark color fabric: print NPP-688C as background then print cracking paste (clear 70~80% + white 30~20%). It can move fabric after cracking in flat table
- Coloring: Mix with PRC series or W series, adding <8%
- Curing: After cracking, leave 1~2 days natural dry and hot press before washing.
- Hot press: 120~140°C, 10~12 secs, .

#### Remarks

- Products are used for textile printing for water based only; must be stored air-tight after opening to prevent property changes.
- Customer is always recommended to perform test prior to bulk application.
- This TDS is meant as a reference, not a warrantee.
- After six to eight months of storage, please shake well before use. Sediment or oil-water

**BEST CHEM CO., LTD.** separation is normal. It will not affect or change the quality.

Tel. +886-3-3222667 Email [service@chemical.com.tw](mailto:service@chemical.com.tw)  
No.15, Ln. 192, Sec. 2, Nanshan Rd., Luzhu Dist., Taoyuan City 33860, Taiwan

[www.chemical.com.tw](http://www.chemical.com.tw)